

TABLE 1

Sample name	Storage Conditions	Fog	S (0.3)	G
Sample 1	Initial value	0.12	+0.25	15.3
	50°C, 40%RH, 3 days	0.12	+0.25	15.7
	50°C, 75%RH, 3 days	0.14	+0.29	17.2
Comparative Sample A	Initial value	0.14	±0 (Reference)	17.1
	50°C, 40%RH, 3 days	0.18	+0.02	16.6
	50°C, 75%RH, 3 days	0.33	-0.14	12.8

IN THE CLAIMS:

Please cancel claim 16 without prejudice to or disclaimer of the subject matter contained therein.

Please amend the claims as follows:

1. (Amended) A heat-developable image-recording material comprising on a support:

a silver-supplying layer containing an organic silver salt, a reducing agent, an organic binder and photosensitive silver halide in an amount that is 10 wt% or less of a coated amount of photosensitive silver halide in the photosensitive layer; and

a separate photosensitive layer containing a photosensitive silver halide;

the heat-developable image-recording material further
containing an electron-transfer agent.
